

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
8 January 2004 (08.01.2004)

PCT

(10) International Publication Number
WO 2004/002892 A1

(51) International Patent Classification⁷:
31/00, C01B 25/32, C04B 14/30

C01G 3/00,

(74) Agent: WEICKMANN & WEICKMANN; Postfach 860
820, 81635 München (DE).

(21) International Application Number:

PCT/EP2003/006849

(22) International Filing Date: 27 June 2003 (27.06.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

02014451.5

28 June 2002 (28.06.2002)

EP

02019542.6

30 August 2002 (30.08.2002)

EP

(71) Applicant (for all designated States except US): MAX-
PLANCK-GESELLSCHAFT ZUR FÖRDERUNG
DER WISSENSCHAFTEN E.V. [DE/DE]; Hofgarten-
strasse 2, 80539 München (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): KAZIN, Pavel,
E. [RU/RU]; Svoboyst. 42-14, Moscow, 123364 (RU).
KARPOV, Andrei, S. [RU/DE]; Heisenbergstr. 1, 70569
Stuttgart (DE). JANSEN, Martin [DE/DE]; Berghalde
18/1, 71229 Leonberg (DE).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC,
SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA,
UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: CERAMIC PIGMENTS ON APATITE BASIS

(57) Abstract: The present invention relates to compounds on apatite basis, having the general formula $M_5(AO_4)_3X$ wherein X is situated in the hexagonal channels of the apatite structure and includes Cu-atoms, processes for the preparation thereof as well as applications of these compounds. The compounds presented herein are particularly useful as pigments.

WO 2004/002892 A1

Ceramic pigments on apatite basis

Description

5

The present invention relates to compounds on apatite basis, processes for the preparation thereof as well as applications of these compounds. The compounds presented herein are particularly useful as pigments.

10 Ceramic pigments are widely used to impart color and / or opacity to artificial articles and are usually incorporated as fine particles in paints, plastics, and other materials. Although many chemical compounds are effectively applied as pigments there is still a need to find new compounds and mixtures which show bright colors and are relatively cheap, stable
15 towards heating and light, chemically compatible with the materials, non-toxic and environment friendly.

A compound with approximate composition $\text{Sr}_5(\text{VO}_4)_3(\text{CuO})$ (1) has been synthesized and structurally characterized by W.Carrillo-Cabrera, H.G. von
20 Schnering, Z. anorg. Allg. Chem. 1999, 625, 183. However the compound was colorless and contained copper in oxidation state +1 only. In the same paper an isostructural compound $(\text{Sr}_{0.9}\text{Ca}_{0.1})_5(\text{Cr}^{\text{V}}\text{O}_4)_3(\text{Cu}^{\text{I}}\text{O})$ is mentioned, the data for it being unpublished. A copper containing strontium vanadate has been described earlier by P.E.Kazin, M.A.Uskova,
25 Yu.D.Tretyakov, M.Jansen, S.Scheurell, E.Kemnitz, Physica C 1998, 301, 185. But only the metal element ratio and the unindexed powder diffraction pattern have been reported then. So far, copper has been introduced in the phosphate apatites only in M position. The solid solution $(\text{M}_{1-x}\text{Cu}_x)_5(\text{PO}_4)_3\text{OH}$, where $\text{M} = \text{Sr}, \text{Ca}$, as well as the fully substituted
30 compound $\text{Cu}_5(\text{PO}_4)_3\text{OH}$ have been reported by M. Pujari, P.N.Patel, J. Solid State Chem. 1989, 83, 100. Besides, the phosphor $\text{Sr}_5(\text{PO}_4)_3\text{Cl}$ doped

- 2 -

by small amount of Cu as activator is known (Hunt, McKeag, J. Electrochem. Soc. 1959, 106, 1032).

Therefore, it was an object of the invention to provide new compounds on
5 apatite basis, especially compounds which are brightly colored.

According to the invention this object is achieved by providing a compound having the general formula (I)



10 wherein the group $M_5(AO_4)_3$ forms an apatite structure and X is situated in the hexagonal channels of the apatite structure and includes Cu-atoms, with the proviso that the compound is not $Sr_5(VO_4)_3(CuO)$, $Sr_5(VO_4)_3(Cu_{0.894}O_{0.952})$, or $(Sr_{0.9}Ca_{0.1})_5(Cr^VO_4)_3(CuO)$.

15 In particular, the invention relates to new chemical compounds, processes of their preparations and applications. The compounds have apatite based structures with general composition $M_5(AO_4)_3X$ where M and A are different individual chemical elements or mixtures of elements appropriate to form the apatite structure.

20

In a preferred embodiment A represents P, V or a mixture thereof and M represents Ba, Sr, Ca or a mixture thereof. X represents different atoms in different quantity, situated in the hexagonal channels. Essential feature of the compounds is the presence of Cu, in particular, of Cu ions in the
25 channels. Most preferably, the Cu ions form O-Cu-O linear units.

The compounds of the invention, in particular, compounds having Cu^{2+} in an unusual two-fold coordination, are brightly colored from dark-blue through blue-violet to red-violet. The color shade can be regulated by using
30 different M and A elements, the brightness can be increased or decreased by oxidizing or reducing the copper ions via annealing in atmosphere with different partial oxygen pressure. The compounds are stable in ambient

- 3 -

conditions and toward heating above 1000 °C in air. The compounds with certain M, A and X are relatively cheap, non-toxic and environment friendly. The compounds are preferably applied as pigments for plastics, paints, cements and plasters.

5

The group X preferably has a charge of -1 and formally represents a certain fraction of Cu^{2+} , and/or Cu^{+} , and O^{2-} ions mixed with anions such as OH^{-} , F^{-} , Cl^{-} , Br^{-} . Most preferably, X represents $\text{Cu}_x\text{O}_y\text{H}_z$, wherein $0 < x \leq 0.85$, $0 \leq z < 1$ and $0.5 < y \leq 1$. More preferably, X represents $\text{Cu}_x\text{O}_y\text{H}_z$,
10 wherein $0.1 \leq x \leq 0.6$, in particular, $0.2 \leq x \leq 0.5$.

15

Several samples of compounds of the invention were characterized by X-ray single crystal and powder diffraction, ICP-OES analysis, scanning electron microscopy with EDX analysis, IR and NMR spectroscopy, magnetic measurements, UV-VIS spectrometry (diffuse reflectance spectra).

20

25

30

In preferred embodiments the main new features of the compounds claimed in the invention are: (i) copper(II) exists in the hexagonal channels of the apatite structure and provides the bright color of the samples; or/and (ii) copper ions are present in the hexagonal channels of phosphate apatites and other compounds with apatite structure; or/and (iii) copper atoms as oxocuprate ions form a continuous solid solution in the hexagonal channels, optionally together with other anions. Essentially unexpected is the incorporation of copper-oxygen units in the place of hydroxyls in the well known phosphate apatites, as well as the presence of divalent copper in the channels in twofold coordination by oxygen atoms. According to (ii) copper ions in an oxidation state of +1, +2 or both, are in the channels of apatites. Examples of apatites are phosphate apatites as well as vanadate apatites. By selecting appropriate elements for A also apatite structures based on SiO_4^{2-} , SiO_4^{4-} and AsO_4^{3-} can be prepared.

- 4 -

It has been reported that in channels of the particular apatite $\text{Sr}_5(\text{VO}_4)_3\text{CuO}$ long, ideally infinite, linear chains of $\text{Cu}_n\text{O}_{n+1}^{(n+2)-}$ are present. According to (iii) above Cu-O^- units can be continuously substituted by anions present in apatites such as OH^- , F^- or Cl^- so that the long $[\text{CuO}]_n^{n-}$ chains are broken
5 into short entities such as monomeric O-Cu-O^3- , O-Cu-O^{2-} , HO-Cu-O^{2-} or oligomeric $\text{O-(Cu-O)}_n\text{-Cu-O}$, wherein n is an integer from 1 to 10, preferably from 1 to 5, and more preferably from 1 to 3.

Compounds containing Cu^{2+} and, in particular, compounds containing Cu^{2+}
10 as well as Cu^+ are brightly colored. They can be used, in particular, as pigments, e.g. as ceramic pigments.

Further, the compounds of the invention, in particular, compounds having only Cu^+ and no Cu^{2+} in group X preferably can be used as intermediates.
15 From these compounds colored substances can be obtained, e.g. by oxidation. To impart color or to enhance color it is often sufficient to oxidize only a small part of Cu(I) to Cu(II) .

The compounds according to the invention can easily be prepared by
20 mixing compounds comprising the elements M, A and X and thermally treating the mixture in a range of from 200 to 1700°C to yield a compound of general formula (I). The starting compounds preferably are employed in a ratio close to the desired stoichiometric ratio. The thermal treatment preferably takes place at 400 to 1500°C, more preferably from
25 700 to 1400°C. The thermal treatment can be performed for 0.01 to 60 h, more preferably from 0.1 to 30 h, and most preferably from 1 to 10 h. To enhance the yield of the desired compounds the thermal treatment can be performed with intermediate regrinding. Depending on the amount of Cu^{2+} desired, the thermal treatment can be performed in an oxygen-containing
30 atmosphere such as air or oxygen or in an oxygen-free atmosphere such as under argon, nitrogen or another protective gas. To enhance the amount of Cu^{2+} present in the hexagonal channels of the apatite, an additional step

can be performed comprising a thermal treatment of the compound in oxygen, inert gas atmosphere or vacuum at 500 to 900°C, preferably from 600 to 800°C for 0.5 to 24 h, preferably from 2 to 12 h.

5 In a most preferred embodiment the process according to the invention comprises the steps:

- (i) mixing of carbonates of M, $(\text{NH}_4)\text{H}_2\text{PO}_4$ and Cu compounds,
- (ii) thermal treatment of this mixture in solid state in air at 600 to 850°C for 1 to 5 h,
- 10 (iii) regrinding,
- (iv) thermal treatment at 1100 to 1400°C for about 1 to 24 h,
- (v) cooling, and
- (vi) regrinding.

15 The compounds $\text{M}_5(\text{AO}_4)_3\text{X}$ preferably can be prepared from mixtures of salts and oxides containing the required components in close to stoichiometric ratio by solid state reaction at about 700 - 1400 °C, or by melting and solidification at about 1000 - 1700 °C. The samples prepared in air contain simultaneously Cu^+ and Cu^{2+} ions. Depending on the copper
20 content and thermal treatment conditions separate linear O-Cu-O or/and condensed (-)O-Cu-O-Cu-O(-) units form in the hexagonal channels. The copper can be further oxidized by annealing in oxygen atmosphere or reduced by annealing in argon atmosphere or vacuum with a Cu_2O - CuO getter.

25

In particular, samples containing Cu^{2+} exhibit an unexpectedly bright color for copper ions. The absorption spectra show overlapping bands in the visible region. They can be related to d-d electron transitions in linear O-Cu(II)-O units. The latter appear to be the first example of twofold
30 coordinated divalent copper in the solid state. The color is changing from dark-blue for $\text{Ba}_5(\text{PO}_4)_3\text{Cu}_x\text{OH}_z$ through blue-violet for $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_x\text{OH}_z$ till red-violet for $\text{Ca}_5(\text{PO}_4)_3\text{Cu}_x\text{OH}_z$. The brightest color is attained for x about

- 6 -

0.1 - 0.4. The color intensity is further increased by annealing the samples in oxygen at 600 - 800 °C.

The compounds of the invention preferably are stable in air at ambient conditions, insoluble in water, and resistant to heating up to 1000 °C. Compounds with $M = \text{Sr, Ca}$, $A = \text{P}$, and $X = \text{Cu}_x\text{OH}_z$ are non-toxic. Among them, the compounds with $M = \text{Ca}$ are very cheap and environment friendly, as they represent simply hydroxylapatite modified by inserting small amounts of copper into the hexagonal channels. Further, the compounds of the invention are stable in alkaline media due to the basic nature of hydroxylapatites.

The invention further relates to a pigment comprising a compound of the invention, in particular, a compound of general formula (I), wherein X comprises Cu^{2+} , more preferably, wherein X comprises Cu^{2+} as well as Cu^+ .

The compounds of the invention can be used as intermediates for preparation of colors as well as colored materials themselves. Therefore, they can be used, e.g. as pigments, paint or as coloring additives, e.g. in cements or plasters.

The following Figures and Examples illustrate this invention.

Fig.1 shows diffuse reflectance spectra of the samples of Example 1. $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_x\text{OH}_y$; as prepared: A1, $x = 0.1$, A3, $x = 0.3$, A5, $x = 0.5$; annealed in oxygen at 800 °C: D1, $x = 0.1$, D3, $x = 0.3$.

Fig.2 shows diffuse reflectance spectra of the samples of Example 4 and Example 5, $\text{M}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$.

Example 1.

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_x\text{OH}_y$, about 1 - 5 g.

5 SrCO_3 , $\text{NH}_4\text{H}_2\text{PO}_4$ and CuO (all of 99,99%) were thoroughly ground and mixed in an agate mortar in a 5.05 : 3 : x molar ratio, where $x = 0.01$, 0.1, 0.2, 0.3, 0.4, 0.5, 0.6. The mixtures were heated stepwise at 600 and 850 °C for 32 h with intermediate regrindings. The powders were
10 pressed in pellets, annealed in air at 1100°C for 24 hours and air-quenched. The pellets were ground in an agate mortar to obtain fine powders.

X-ray diffraction patterns correspond to almost single phase apatite (about 97% for $x = 0.01$ and >99% for the other x). Rietveld structure
15 refinement have confirmed the copper to be situated in the hexagonal channels. Infrared spectra testify presence of OH groups with very weak hydrogen bonds. The samples are blue-violet in color, deepening with increasing x. The diffuse reflectance spectra are shown in Fig.1. Two
20 overlapping lines are observed in the visible region. The samples with $x = 0.1$ and 0.3 were further annealed in oxygen flow at 800 °C for 2 hours. By this treatment, the intensity of the absorption lines has been increased.

Example 2.

25 Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, 5 kg.

20 moles rough crystalline $\text{NH}_4\text{H}_2\text{PO}_4$ and 33.67 moles SrCO_3 were thoroughly ground and mixed for 1 hour in a mill. A water solution of 2 moles $\text{Cu}(\text{NO}_3)_2 \cdot 2.5\text{H}_2\text{O}$ was added and the components were mixed for 1
30 hour again. The mixture was annealed stepwise at 600 °C and 1200 °C for total time of about 36 hours with an intermediate regrinding and air quenched.

The powder obtained is bright blue-violet in color.

Example 3.

5 Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{1/3}\text{O}_{2/3}$, about 1 g.

The sample (about 0.5 g) with $x = 1$ prepared as in Example 1 was arc-melted on a copper plate in air at about 1700 °C for about 1-2 minutes and air quenched. The sample is blue-violet in color and contains > 98% of
10 apatite phase.

Example 4.

Preparation of $\text{M}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, where M is Ca or Ba, about 1 - 5 g.
15

MCO_3 , $\text{NH}_4\text{H}_2\text{PO}_4$ and CuO (all of 99,99%) were thoroughly ground and mixed in an agate mortar in a 5.05 : 3 : 0.3 molar ratio. The mixtures were annealed stepwise at 600, 850 °C and 1100 °C for total time of about 60 - 80 hours with intermediate regrindings and air quenched.
20

The sample with Ca is red-violet in color, and the one with Ba is dark-blue. The corresponding diffuse reflectance spectra are shown in Fig.2.

Example 5.

25 Preparation of $\text{Sr}_{2.5}\text{M}'_{2.5}(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$.

The same preparation procedure as in Example 4 but instead of MCO_3 an equimolar mixture of SrCO_3 and $\text{M}'\text{CO}_3$ was used.
30

The samples have intermediate colors between these of the samples of Example 2 and Example 4. The diffuse reflectance spectrum of the sample with $M' = \text{Ca}$ is shown in Fig.2.

5 Example 6.

Preparation of $M_5(\text{VO}_4)_3\text{Cu}_{0.3}\text{O}_{1-2}\text{H}_y$, where M is Sr or Ca.

10 The same preparation procedure as in Example 4, but $1/2 \text{V}_2\text{O}_5$ was taken instead of $\text{NH}_4\text{H}_2\text{PO}_4$.

As obtained apatite phases have gray-blue-violet ($M = \text{Sr}$) or light-gray-green ($M = \text{Ca}$) colors.

15 Example 7.

Preparation of $M_5(\text{PO}_4)_3\text{Cu}_x(\text{O},\text{X})_y\text{H}_z$,
, where M is Ca or Sr, X is F or Cl.

20 The same preparation procedure as in Example 4, but 0.2 - 0.7 mol of NH_4X was added to the initial mixture.

The samples show colors ranging from pink to blue-violet.

25 Example 8.

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, ca. 250 g.

30 1 mole $\text{NH}_4\text{H}_2\text{PO}_4$ and 1.68 mole SrCO_3 were thoroughly ground and mixed for 1 hour in a mill. A water solution of 0.1 mole $\text{Cu}(\text{NO}_3)_2 \cdot 2.5\text{H}_2\text{O}$ was added and the components were mixed for 1 hour again. The mixture was

- 10 -

annealed stepwise at 600 °C and 1100 °C for total time of about 24 hours in a rotary kiln (Al_2O_3 tube, $d_i = 12$ cm, $l = 50$ cm, rotation speed 1 min^{-1}). Thereafter the furnace tube was inclined so that by rotation the powder came down and fell into a cold container. After cooling, the powder collected in the container was reground.

The powder obtained is bright blue-violet in color.

Example 9

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, 1-10 g.

SrCO_3 , $\text{NH}_4\text{H}_2\text{PO}_4$ and $\text{Cu}(\text{NO}_3)_2 \cdot 2.5\text{H}_2\text{O}$ (all of 99% purity) were thoroughly ground and mixed in an agate mortar in a 5.05:1:0.3 molar ratio. The mixture was heated at 600°C for 6 hours. Then the reground mixture was placed in a tube furnace equipped with different operating atmosphere modes and heated in an air-flow at 1100°C for 3 hours. Thereafter the working temperature was decreased to 1000°C, the operating atmosphere was changed to dry-air, and the mixture was further cooled down to room temperature. The rate of cooling steps in both cases was programmed to be 200°C/h.

The powder is bright blue-violet.

Example 10

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, 1-10 g.

The same preparation procedure as in Example 9, but after changing atmosphere to dry-air the furnace was switched off.

The sample is bright blue-violet.

Example 11

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, about 1-10 g.

- 5 The same preparation procedure as in Example 9, but with an extra post-annealing of the mixture in an oxygen flow at 600°C for 2 hours.

The color of the sample is the same as in Example 9, but brighter.

10 Example 12

Preparation of $\text{Sr}_5(\text{PO}_4)_3\text{Cu}_{0.3}\text{OH}_y$, about 1-10 g.

- 15 The same preparation procedure as in Example 9, but the cooling of the mixture in dry-air was performed only down to 600°C, afterwards the operating atmosphere was changed to oxygen, the mixture was heated at 600°C for 2 hours, and further cooled down to room temperature.

The color of the sample is the same as in Example 9, but brighter.

Claims

1. A compound having the general formula (I)
5 $M_5(AO_4)_3X$,
wherein the group $M_5(AO_4)_3$ forms an apatite structure and X is situated in the hexagonal channels of the apatite structure and includes Cu-atoms, with the proviso that the compound is not $Sr_5(VO_4)_3(CuO)$, $Sr_5(VO_4)_3(Cu_{0.894}O_{0.952})$, or $(Sr_{0.9}Ca_{0.1})_5(Cr^VO_4)_3(CuO)$.
10
2. The compound according to claim 1, wherein A represents P, V or a mixture thereof and M represents Ba, Sr, Ca or a mixture thereof.
3. The compound of claim 1, wherein X represents a mixture of Cu^{2+} ,
15 Cu^+ , O^{2-} , OH^- , F^- , Cl^- , Br^- and/or I^- .
4. The compound of claim 1, wherein X comprises copper ions.
5. The compound according to any of the preceding claims, wherein X
20 comprises Cu^{2+} .
6. The compound according to any of the preceding claims, wherein linear units O-Cu-O are present in the hexagonal channels of the apatite structure.
25
7. The compound according to any of the preceding claims, wherein X represents $Cu_xO_yH_z$, wherein $0 < x \leq 0.85$, $0 \leq z < 1$ and $0.5 < y \leq 1$.
8. The compound according to any of the preceding claims, wherein
30 $0.1 \leq x \leq 0.6$.

- 13 -

9. The compound according to any of the preceding claims, wherein A represents P.
10. A process for preparing a compound according to any of claims 1-9 comprising the steps:
- (i) mixing of compounds comprising the elements M, A and X,
 - (ii) thermal treatment of the mixture in the range of 200 to 1700°C to yield a compound of the general formula (I).
11. The process according to claim 10, wherein the thermal treatment is performed for 0.01 to 60 hours.
12. The process according to claim 10 or 11, wherein the thermal treatment is performed with intermediate regrinding.
13. The process according to any of claims 10 to 12, wherein the thermal treatment of the mixture is performed in air, argon or oxygen.
14. The process according to any of claims 10 to 13, further comprising the step
- (iii) thermal treatment of the compound obtained in step (ii) in oxygen, inert gas atmosphere or vacuum at 500 to 900°C for 0.5 to 24 hours.
15. The process according to any of claims 6 to 12 comprising the steps
- (i) mixing of carbonates of M, $(\text{NH}_4)\text{H}_2\text{PO}_4$ and Cu-compounds,
 - (ii) thermal treatment of this mixture in solid state in air at 600 to 850°C for 1 to 5 hours,
 - (iii) regrinding,
 - (iv) thermal treatment at 1100 to 1400°C for about 1 to 24 hours,

- 14 -

- (v) cooling and
- (vi) regrinding.

16. Pigment comprising a compound to any of claims 1 to 9.

5

17. Pigment according to claim 15, wherein X in the compound of general formula (I) comprises Cu^{2+} .

18. Use of a compound according to any of claims 1 to 7 as pigment,
paint or as coloring additive in cements or plasters.

10




Fig. 1.




Fig.2.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 03/06849

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C01G3/00 C01G31/00 C01B25/32 C04B14/30

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C01G C01B C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ, CHEM ABS Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	<p>P. E. KAZIN, A. S. KARPOV, M. JANSEN, J. NUSS, Y. TERTYAKOV: "Crystal structure and properties of strontium phosphate apatite with oxocuprate ions in hexagonal channels"</p> <p>Z. ANORG. ALLG. CHEM., vol. 629, 31 January 2003 (2003-01-31), page 344-352 XP009017125 the whole document</p> <p style="text-align: center;">---</p> <p style="text-align: center;">-/--</p>	1-18

☒ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

29 September 2003

Date of mailing of the international search report

13/10/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5618 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Nobis, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 03/06849

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>W. CARRILLO-CABRERA, H. G. VON SCHNERING: "Pentatronstium Tris'tetraoxovanadate(V)! catena-Monoxocuprate(I), $\text{Sr}_5(\text{VO}_4)_3(\text{CuO})$ - an apatite derivative with inserted linear 'CuO!1- chains" Z. ANORG. ALLG. CHEM., vol. 625, 1999, page 183-185 XP009017131 cited in the application the whole document</p> <p style="text-align: center;">---</p>	1
A	<p>P. PATEL, O. AGRAWAL: "Preparation and characterisation of mixed (Ca+Ba+Cu) hydroxylapatites" J. INDIAN CHEM. SOC., vol. 61, no. 10, 1984, pages 906-907, XP009017132 the whole document</p> <p style="text-align: center;">-----</p>	1